



Ultraplan Eco



**Ultra-fast hardening
self-levelling
compound with very
low VOC (volatile
organic compound)**

CLASSIFICATION ACCORDING TO EN 13813

The smoothing compounds prepared with **Ultraplan Eco** in compliance with the prescriptions present in this very technical data sheet are classified as CT-C25-F7-A2fl according to European Norm 13813.

WHERE TO USE

Ultraplan Eco is used for levelling and removing differences in thickness from 1 to 10 mm on new or existing substrates, preparing them to receive any kind of flooring where an excellent resistance to loads and traffic is needed.

Ultraplan Eco is particularly suitable for areas subject to wheeled chairs.

Ultraplan Eco is for interior use only.

Some application examples

- Levelling concrete slabs or screeds based on cement, **Mapecem**, **Mapecem Pronto**, **Topcem**, **Topcem Pronto**, anhydrite and magnesite, including those with underfloor heating systems incorporated.
- Levelling existing cement, terrazzo, ceramic and natural stone floors.

TECHNICAL CHARACTERISTICS

Ultraplan Eco is a grey powder consisting of special cements with fast setting and hydration together with graded silica sand, resins and special additives, according to a formula developed in the MAPEI Research Laboratories.

Mixed with water **Ultraplan Eco** becomes a highly fluid and easily workable mortar, perfectly self-levelling with high adhesion to the substrate that dries ultra-quickly.

Ultraplan Eco can be applied with an automatic pressure pump for distances over 100 m.

Ultraplan Eco can be spread in thicknesses up to 10 mm per coat without shrinkage, cracking or crazing, and develops very high compressive and flexural strength, as well as resistance to indentation and abrasion.

Ultraplan Eco is ready to receive flooring after approximately 12 hours, regardless of the thickness.

It is recommended to wait 24 hours when installing wooden flooring.

Ultraplan Eco has very low emissions of volatile organic compounds (EMICODE EC1) and is harmless to the health of the installer and the end-user in the areas where applied.

RECOMMENDATIONS

- Do not add water to a mix which has already started to set.
- Do not add lime, cement or gypsum to the mix.
- Do not use **Ultraplan Eco** for exterior applications.
- Do not use **Ultraplan Eco** on substrates subject to continuous rising damp.
- If a coat of **Ultraplan Eco** needs to be applied once the preceding one is completely dry, first apply **Eco Prim T**.
- Do not apply **Ultraplan Eco** at temperatures below +5°C.

Ultraplan Eco



Mixing Ultraplan Eco -
Mirabello kindergarten -
Cantù (Como) - Italy



Polishing with
helicopter before
applying Ultraplan Eco -
Mirabello kindergarten -
Cantù (Como) - Italy



Linoleum applied on
screed previously
levelled with Ultraplan
Eco - Mirabello
kindergarten - Cantù
(Como) - Italy

TECHNICAL DATA (typical values)		EN 13813 CT-C25-F7-A2 ^{II}
PRODUCT IDENTIFICATION		
Consistency:	fine powder	
Colour:	grey	
Bulk density (kg/m ³):	1300	
Dry solids content (%):	100	
Storage:	12 months in original sealed packaging in a dry place	
Hazard classification according to EC 1999/45:	none. Before using refer to the "Safety instructions for preparation and application" paragraph and the information on the packing and Safety Data Sheet	
EMICODE:	EC1 - very low emission	
Custom class:	3824 50 90	
APPLICATION DATA (at +23°C - 50% R.H.)		
Thickness per coat:	from 1 to 10 mm (minimum of 3 mm before the installation of wooden floors)	
Mixing ratio:	24-25 parts of water per 100 parts by weight of Ultraplan Eco	
Self levelling:	yes	
Density of mix (kg/m ³):	2000	
pH of mix:	approx. 12	
Application temperature range:	from +5°C to +35°C	
Open time:	20-30 minutes	
Setting time:	45-60 minutes	
Set to light foot traffic:	3 hours	
Time before laying flooring:	12 hours (24 hours for wooden floors)	
FINAL PERFORMANCE DATA		
Compressive strength (N/mm ²):		
- after 1 day:	12.0	
- after 3 days:	17.0	
- after 7 days:	20.0	
- after 28 days:	26.0	
Flexural strength (N/mm ²):		
- after 1 day:	3.0	
- after 3 days:	4.0	
- after 7 days:	5.0	
- after 28 days:	7.0	
Resistance to abrasion TABER Abrasimer (Abrading wheel H22-500 g-200 revolutions) expressed as weight loss (g):		
- after 7 days:	2.8	
- after 28 days:	2.3	
Brinell hardness:		
- after 1 day:	55	
- after 3 days:	70	
- after 7 days:	80	
- after 28 days:	100	

- Do not apply **Ultraplan Eco** in thicknesses less than 3 mm when wooden flooring needs to be installed.

APPLICATION PROCEDURE

Preparing the substrate

Substrates must be completely dry, sound, free from dust, loose parts, paint, wax, oil, rust and traces of gypsum.

Cement based surfaces not sufficiently sound must be removed or, where possible, reinforced with **Eco Prim PU 1K**, **Prosfas** or **Primer MF**.

Fissures in concrete substrates must be repaired with **Eporip**.

Dusty or very porous concrete surfaces must be treated with a coat of **Eco Prim T**, diluted with water 1:1, or **Primer G**, diluted with water 1:3 (both primers have very low emission of volatile organic compounds - EMI CODE EC1) in order to even out the absorbency of the substrate.

Anhydrite screeds can be levelled with **Ultraplan Eco** only after the application of a coat of **Eco Prim T** diluted with water 1:1.

First apply a coat of undiluted **Eco Prim T** on ceramic or natural stone surfaces after the surface has been cleaned with detergents and mechanically abraded.

Preparing the mix

Pour a 23 kg bag of **Ultraplan Eco** into a bucket containing approximately 5.6 litres of clean water and mix with a low speed electric mixer to obtain an homogeneous lump-free mix.

Larger quantities can be prepared in on-site cement mixers.

After 2-3 minutes of slackening, restir the mix. The mix is then ready to be used.

It is recommended to add approximately 20-30% of 0/4 or 0/8 grain sand when **Ultraplan Eco** is used for thicknesses more than 10 mm (max. 20 mm). For further information consult MAPEI Technical Advisory Department.

The quantity of **Ultraplan Eco** mixed at any time must be used within 20-30 minutes (at +23°C).

Spreading the mix

Apply **Ultraplan Eco** in a single coat from 1 to 10 mm with a large metal trowel or rake and keeping the trowel slightly inclined to obtain the desired thickness.

Ultraplan Eco can also be applied with an automatic pressure pump for renders.

Due to its remarkable self-levelling properties **Ultraplan Eco** immediately loses small imperfections (trowel marks, etc.).

When a second coat of **Ultraplan Eco** is required, it is recommended to apply it as soon as the first one is set to light foot traffic (approximately 3 hours at +23°C).

Ultraplan Eco is suitable to receive resilient, carpet, and ceramic floor coverings fixed

after 12 hours at +23°C (the time can vary, depending on the room temperature and humidity). When installing wood flooring, wait 24 hours.

Check the humidity content with a carbide hygrometer or an electric moisture meter, keeping in mind that the latter only gives indicative values.

Cleaning

While still wet, **Ultraplan Eco** can be removed from tools with water.

CONSUMPTION

1.6 kg/m² per mm of thickness.

PACKAGING

Ultraplan Eco is available in 23 kg bags.

STORAGE

Ultraplan Eco stored in a dry place is stable for at least 12 months. However, with time it could undergo a slower setting time but the final characteristics do not alter.

Manufactured in compliance with the regulations of the 2003/53/EC Directive.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Contains cement that in contact with sweat or other body fluids produces and irritant alkaline reaction. Use gloves and protective goggles. For further information refer to the safety data sheet.

PRODUCT FOR PROFESSIONAL USE.

WARNING

Although the technical details and recommendations contained in this data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical applications; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.



Carpet laid on a hotel corridor after levelling with **Ultraplan Eco** - Hotel Renaissance - Austria



This symbol shows our commitment to the environment. More than 110 MAPEI products, featuring the "Green innovation" mark, help to contribute valuable points toward LEED-certified projects.



This symbol is used to identify MAPEI products which give off a low level of volatile organic compounds (VOC) as certified by GEV (Gesellschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e.V.), an international organisation for controlling the level of emissions from products used for floors.

All relevant references for the product are available upon request and from www.mapei.com

Ultraplan Eco



513-11-2008

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

(GB) A.G. BETA